



City Cat House, 29, Police Court Lane, Fort, G.P.O. Box No. 1343, Mumbai – 400 001. (India)
 Tel.: 00-91-22-2265 1703 / 2265 1704 / 2262 2443 · Fax: 00-91-22-2263 0348 / 2265 0815 / 2265 7891.
 E-mail: citycat@vsnl.com · info@citycatpigments.com · Website: <http://www.citycatpigments.com>.

Driers

LEAD OCTOATE

Parameters	Lead Octate 36%	Lead Octoate 33%
Appearance	Straw coloured clear liquid	Straw coloured clear liquid
Colour	4 Gardner max	4 Gardner max
Metal content as Pb	36±0.2%	33±0.2%
Sp. Gravity @ 30°C	1.36±0.05	1.28±0.05
NVM @ 120°C For 60 Mints.	75±5%	69±5%
Viscosity @ 30°C In Ford cup B-4.	50 sec. Max	35 sec. Max
Flash Point	45°C	45°C
MTO tolerance V/V	1:19	1:19

COBALT OCTOATE

Parameters	Cobalt Octoate 10%	Cobalt Octoate 6%	Cobalt Octoate 4%
Appearance	Clear purple blue liquid	Clear purple blue liquid	Clear purple blue liquid
Colour	NA	NA	NA
Metal content as Co	10±0.2%	6±0.2%	4±0.2%
Sp. Gravity @ 30°C	1.00±0.05	0.90±0.05	0.85±0.05
NVM @ 120°C For 60 Mints.	65 Max.	40 Max.	30 Max.
Viscosity @ 30°C In Ford cup B-4	65 sec. Max	20 sec. Max	15 sec. Max
Flash Point	45°C	45°C	45°C
MTO tolerance	1:19	1:19	1:19

MANGANESE OCTOATE

Parameters	Manganese Octoate 10%	Manganese Octoate 6%
Appearance	Brown coloured clear liquid	Brown coloured clear liquid
Metal content as Mn	10±0.2%	6±0.2%
Sp. Gravity @ 30°C	0.99±0.05	0.99±0.05
NVM @ 120°C For 60 Mints.	65±5	40±5
Viscosity @ 30°C In Ford cup B-4	45 Mints Max	35 sec Max
Flash Point	45°C	45°C
MTO tolerance	1.19	1.19

CALCIUM OCTOATE

Parameters	Calcium Octoate 10%	Calcium Octoate 6 %	Calcium Octoate 3 %
Appearance	Clear liquid	Clear liquid	Clear liquid
Colour	6 Gardner Max	4 Gardner Max	3 Gardner Max
Metal as Ca	10±0.2%	6±0.2%	3±0.2%
Sp. Gravity @ 30°C	1.03±0.05	0.91±0.05	0.87±0.03
NVM @ 120°C for 60 Mints.	65 Max.	40±5	35 Max.
Viscosity @30°C in Ford cup B-4	40 sec. Max	25 sec. Max	20 sec. Max
Flash Point	45°C	45°C	45°C
MTO tolerance	1:19	1:19	1:19

ZIRCONIUM OCTOATE

Parameters	Zirconium Octate 18 %	Zirconium Octoate 6 %
Appearance	Straw coloured clear liquid	Straw coloured clear liquid
Colour	6 Gardner max	6 Gardner max
Metal content as Zr	18±0.2%	6±0.2%
Sp. Gravity @ 30°C	1.1±0.05%	0.87±0.05%
NVM @ 120°C For 60 Mints.	70 max	25±5
Viscosity @ 30°C In Ford cup B-4.	30 sec. Max	15 sec. Max
Flash Point	45°C	45°C
MTO tolerance V/V	1:19	1:19

ZINC OCTOATE

Parameters	Zinc Octate 12 %	Zinc Octoate 6 %
Appearance	Clear liquid	Clean liquid
Colour	4 Gardner max	3 Gardner max
Metal content as Zn	12±0.2%	6±0.2%
NVM @ 120°C For 60 Mints.	60±5%	30±5%
Viscosity @ 30°C	30 sec. Max	15 sec. Max
Specific gravity @ 30°C	0.96±0.05	0.86±0.05
Flash Point	45°C	45°C
MTO tolerance	1:19	1:19