

CATONE FANAL PINK – PIGMENT RED 169

Product Description:

| | |
|----------------|-------------------|
| Trade Name | Catone (Toner) |
| Product | Catone Fanal Pink |
| C.I. Name | Pigment Red 169 |
| C.I. No | 45160:2 |
| CAS NO | 12224-98-5 |
| Chemical Class | Xanthene |
| E.U. No | 235-469-2 |
| Hue | Bright Bluish Red |


Full Strength



Reduction 1:10



Chemical Structure:



Application:

| | |
|-----|---|
| Ink | Water Based Flexographic Inks Gravure Inks |
|-----|---|

Standard Packing:

| |
|---|
| - 20/25 Kgs HDPE Bags /Paper Bags |
| - Different Types of Packaging available on request |

| Physical Properties: | |
|---------------------------------------|-----|
| Specific Gravity | 1.4 |
| Oil Absorption (gm/100 gms) | 65 |
| pH | 7 |
| Fastness Properties: | |
| Heat Resistance 180°C (355°F) 10 mins | 3 |
| Water | 4 |
| 5% Acid (HCl) | 1 |
| 5% Alkali (NaOH) | 1 |
| Ethanol | 2 |
| N-Butanol | 2 |
| N-Butyl Acetate | 5 |
| M.E.K. | 3 |
| Light (Full Strength) | 6 |
| Light (Reduction) | 3 |

The above shades have been generated electronically and should therefore not be used for comparison purposes. The information mentioned herein are based on our current knowledge and cannot be taken as guarantee. The data mentioned herein are indicative without warranty and are meant only for guidance. It is recommended that customer should test the products under actual conditions in particular application and we do not accept any liability relating to use of our product.